

Provisional technical data sheet

Advanced Materials

Araldite[®] CW 2710-1	100	pbw
Aradur[®] HW 2711-1	100	pbw

Liquid, prefilled, flame retardant, hot-curing two-component epoxy casting system with excellent thermal conductivity.

Application

Potting of motors, generators, actuators, modules and sensors.

Processing Methods

Automatic pressure gelation process (APG)
Conventional gravity casting process under vacuum.

Key Properties

High thermal conductivity.
Flammability: UL 94 V-0 (12 mm).
Good thermal resistance.
Good resistance to atmospheric and chemical degradation.

Product Data (Guideline Values)

CW 2710-1

High viscosity, highly filled bisphenol A epoxy resin.

Viscosity at 25 °C	ISO 2555	Pa*s	120 – 185 *
Specific gravity at 25 °C	ISO 2811	g/cm ³	1.95 - 2.20 *
Appearance	Visual		Brown

HW 2711-1

High viscosity, highly filled pre-accelerated anhydride hardener.

Viscosity at 25 °C	ISO 2555	Pa*s	25 – 60 *
Specific gravity at 20 °C	ISO 2811	g/cm ³	1.95 - 2.20
Appearance	Visual		Grey

* Specified range (provisional)

Processing Data (Guideline Values)

Mix Ratio

		Parts by weight	Parts by volume
CW 2710-1	Resin	100	100
HW 2711-1	Hardener	100	100

Gel Time, Viscosity and Curing

Mix viscosity at 60 °C	Rheomat MC 20	mPa*s	5'800
Pot life at 60 °C (Time to reach 100 Pas)	Rheomat MC 20	min	400
Gel time at 90 °C	Gelnorm	min	35
Gel time at 100 °C	Gelnorm	min	20
Gel time at 120 °C	ISO 9396	min	6 – 10 *
Minimum curing cycle	1 hour at 90 °C + 1.5 hour at 140 °C		

*Specified range (provisional)

Processing and Storage (Guideline Values)

Preparation and Mixing

CW 2710-1 / HW 2711-1 contain fillers, which tend to settle over time.

It is therefore recommended to carefully homogenize the complete contents of the container before use. The use of ceramic materials is recommended, due to the abrasiveness of the filler.

Measure (by weight or volume) the resin and the hardener. Add the hardener to the resin, making sure that the required amount of hardener is transferred to the resin. Stir thoroughly until mixing is complete.

Air entrainment during mixing results in pores in the cured resin. Mixing under vacuum or in a metering-mixing machine is the most effective way to prevent air entrainment. Alternatively the static resin – hardener mixture may be degassed in a vacuum chamber – allowing at least 200 % ullage for the foam to expand.

General instructions for preparing prefilled resin systems

The two components will be mixed in the desired quantity under vacuum and at slightly elevated temperature (50 - 60°C). For the mixing of medium- to high viscous casting resin systems and for mixing at lower temperatures, we recommend special thin film de-gassing mixers that may produce additional self-heating of 10-15 °C as a result of friction. Depending on quantity, mixer device, mixing temperature and application, the mixing time is 0.5 to 1h, under a vacuum of 1 to 8 mbar.

The premixed components packed according to their mixing ratio, could be used per container. In case of filler sedimentation, it is recommended to empty the container completely. Before partial use, the content must be carefully homogenized at elevated temperature. We recommend the same preheating temperature to prevent air enclosures when discharging the components.

In automatic mixing and metering installations, both components will be degassed and homogenized under a vacuum of about 2 mbar in the holding tanks. When degassed, the prefilled products are stirred up from time to time to avoid any sedimentation. After dosing and mixing with a static mixer, the system is fed directly to the vacuum chamber or, in the automatic pressure gelation process, directly into the hot casting mould. By using circular feeding tubes, several casting stations can be served.

Curing

To determine whether cross-linking has been carried to completion and the final properties are optimal, it is necessary to carry out relevant measurements on the actual object or to measure the glass transition temperature. Different gel and cure cycles in the customer's manufacturing process could lead to a different degree of cross-linking and thus a different glass transition temperature.

Storage Conditions

Store the components in a dry place in tightly sealed original containers. Under these conditions, the shelf life will correspond to the expiry date stated on the label. Partly emptied containers should be tightly closed immediately after use. For information on waste disposal and hazardous products of decomposition in the event of a fire, refer to the Material Safety Data Sheets (MSDS) for these particular products.

Mechanical and Physical Properties (Guideline Values)

Determined on standard test specimen at 23°C. Cured for 1h / 90°C and 1.5h / 140°C.

Color of casting			brownish
Glass transition temperature	ISO 11359-2	°C	120
Thermal class	IEC 60085		H
Density	ISO 1183	g/cm ³	2.1
Flexural strength	ISO 178	MPa	78
Elongation at break	ISO 178	%	0.6
Flexural modulus	ISO 178	MPa	13'000
Hardness	ISO 868	Shore D	92
Critical stress intensity factor	PM 216-0'/89	MPa*m ^{1/2}	2.7
Specific energy at break	PM 216-0'/89	J/m ²	300
Coefficient of thermal expansion	ISO 11359-2		
Alpha 1 < Tg		ppm/K	24
Alpha 2 > Tg			67
Thermal conductivity	ISO 8894	W/m*K	1.7
Flammability	UL 94	E96722	V-0 (12mm)

Electrical Properties (Guideline Values)

Determined on standard test specimen at 23°C. Cured for 1h / 90°C and 1.5h / 140°C.

Dielectric strength (2 mm specimen)	IEC 60243-1	kV/mm	25
Dielectric loss factor (tan δ, 50Hz, 25°C)	IEC 60250	%	1.2
Dielectric constant (ε _r , 50Hz, 25°C)	IEC 60250		4.7
Volume resistivity (ρ, 25°C)	IEC 60093	Ω cm	10 ¹⁴

Legal Notice

Huntsman Advanced Materials

(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials

Email:
advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2014 Huntsman Corporation or an affiliate thereof. All rights reserved.